

# TEXTILES

Técnicos & Decorativos

IRUÑA *TEX*





**Color 03**

**GALATEA**



**Color 01**



**Color 04**



**Color 02**



**Color 05**



**Color 03**

DESIGN: GMB 3071 S2

DATE: 28.11.2023  
REPORT NO: 3337**CERTIFIED**

PREPARED BY	APPROVED
KÜBRA ÜNLÜ PHYSICS LABORATORY	FULYA TUNALI LABORATORY CHIEF

**DESIGN: GMB 3071 S2**

**DATE: 28.11.2023**  
**REPORT NO: 3337**

PROPIEDADES TÉCNICAS	
DISEÑO	GALATEA GMB 3071 S2
ANCHO (CM)	300 ±%1
PESO (GR/M²)(ISO 3801)	230 ±%5
"RESISTENCIA A LA TENSIÓN (URDIMBRE/TRAMA) " (EN ISO 13934-1)	WARP FORCE : 1768 ± %10
	WEFT FORCE : 1042 ± %10
"RESISTENCIA AL DESGARRO (URDIMBRE/TRAMA) " (EN ISO 13937-3)	WARP: 108 ± %10
	WEFT: 108 ± %10

DISEÑO	COLOR	"LIGHT FAST-NE SS"	As (%)	Rs (%)	Ts (%)	gtot-A	Fc-A	gtot-B	Fc-B	gtot- C	Fc-C	gtot- D	Fc-D	Tuv (%)	Tv (%)	Rv (%)
GMB 3071 S2	1	5	19,7	47,43	32,87	0,48	0,56	0,47	0,62	0,42	0,71	0,27	0,84	17,09	29,68	44,33
GMB 3071 S2	2	5	22,04	46,55	31,41	0,48	0,57	0,48	0,63	0,42	0,72	0,27	0,84	16,67	26,68	40,39
GMB 3071 S2	3	5	24,39	44,52	31,09	0,49	0,58	0,49	0,64	0,43	0,73	0,27	0,85	16,65	24,51	36,0
GMB 3071 S2	4	5	24,07	44,88	31,05	0,49	0,58	0,48	0,64	0,43	0,73	0,27	0,85	16,95	24,3	34,8
GMB 3071 S2	5	5	38,24	37,13	24,63	0,53	0,62	0,52	0,68	0,45	0,77	0,28	0,87	10,09	13,34	21,14

<b>PREPARED BY</b>	<b>APPROVED</b>
<b>KÜBRA ÜNLÜ</b> <b>PHYSICS LABORATORY</b>	<b>FULYA TUNALI</b> <b>LABORATORY CHIEF</b>